

測試報告 Test Report

號碼(No.): ETF20C00097

日期(Date): 31-Dec-2020

頁數(Page): 1 of 8

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)
新北市泰山區南林路102號 (NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN)

以下測試樣品係由申請廠商所提供及確認 (The following sample(s) was/were submitted and identified by/on behalf of the applicant as) :

樣品名稱(Sample Description) : NAN YA NON ORIENTED CASTING POLYPROPYLENE FILM (南亞無延伸聚丙烯膜)
樣品包裝/數量(Sample Package/Quantity) : 請參考報告末頁樣品照片 (PLEASE REFER TO THE SAMPLE PHOTO AT THE END OF THE REPORT) / -
樣品保存方式(Sample Packaging) : -
樣品型號(Style/Item No.) : XE(0M0)
樣品批號(Lot. No.) : 1C09D02
樣品材質(Sample Material) : 聚丙烯 (PP)
送樣廠商(Sample Submitted By) : 南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)
送樣廠商地址/電話/連絡人(Company Add/Tel/Contact Person) : -
製造日期(Manufacturing Date) : 20201209
有效日期(Expiry Date) : -

=====
收件日(Sample Receiving Date) : 22-Dec-2020
測試期間(Testing Period) : 22-Dec-2020 to 31-Dec-2020

測試需求 (Test Requested) :
依據客戶指定，參考中華民國食品器具容器包裝衛生標準 (102.08.20部授食字第1021350146號令修正)進行測試。測試項目請參閱測試結果表格。(As specified by client, with reference to Sanitation Standard for Food Utensils, Containers and Packages (MOHW Food No. 1021350146, amended on 2013/08/20) to conduct test. Please refer to the result table(s) for testing item(s).)

測試結果(Test Results) : 請見下一頁。(Please refer to next page(s).)

蕭志祥
蕭志祥 / 副理
化學實驗室 - 台北
台灣檢驗科技股份有限公司
報告簽署人



PIN CODE: 04745B33

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

測試報告 Test Report

號碼(No.): ETF20C00097

日期(Date): 31-Dec-2020

頁數(Page): 2 of 8

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)
 新北市泰山區南林路102號 (NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN)

測試部位敘述(Test Part Description)

No.1 : 透明塑膠膜 (TRANSPARENT PLASTIC FILM)

測試結果(Test Results)

測試項目 (Test Item(s))	測試方法 (Method)	單位 (Unit)	LOQ/ LOD	結果 (Result)	限值 (Limit)
				No.1	
★鉛 / Lead (Pb)	食品器具、容器、包裝檢驗方法-聚丙 烯(PP)塑膠類之檢驗 (107年9月17日衛 授食字第1071901787號公告) · 以感 應耦合電漿放射光譜儀分析。 / With reference to Methods of Test for Food Utensils, Containers and Packages - Test of Polypropylene (PP) Plastic Products (MOHW Food No. 1071901787 announced, September 17, 2018), analysis was performed by ICP-OES.	ppm	5	n.d.	100
★鎘 / Cadmium (Cd)		ppm	0.5	n.d.	100
★鄰苯二甲酸二(2-乙基己基)酯 / DEHP (Di- (2-ethylhexyl) phthalate) (CAS No.: 117- 81-7)	CNS 15138-1 (民國101年) · 以氣相層 析質譜儀分析。 / With reference to CNS 15138-1 (2012), analysis was performed by GC/MS.	%	0.003	n.d.	0.1
★鄰苯二甲酸二丁酯 / DBP (Di-n-butyl phthalate) (CAS No.: 84-74-2)		%	0.003	n.d.	0.1
★鄰苯二甲酸丁苯甲酯 / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7)		%	0.003	n.d.	0.1
★鄰苯二甲酸二異癸酯 / DIDP (Diisodecyl phthalate) (CAS No.: 26761-40-0; 68515- 49-1)		%	0.01	n.d.	0.1
★鄰苯二甲酸二異壬酯 / DINP (Diisononyl phthalate) (CAS No.: 28553-12-0; 68515- 48-0)		%	0.01	n.d.	0.1
★鄰苯二甲酸二甲酯 / DMP (Dimethyl phthalate) (CAS No.: 131-11-3)		%	0.003	n.d.	0.1

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

測試報告

Test Report

號碼(No.): ETF20C00097

日期(Date): 31-Dec-2020

頁數(Page): 3 of 8

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)

新北市泰山區南林路102號 (NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN)

測試項目 (Test Item(s))	測試方法 (Method)	單位 (Unit)	LOQ/ LOD	結果 (Result)	限值 (Limit)
				No.1	
★鄰苯二甲酸二正辛酯 / DNOP (Di-n-octyl phthalate) (CAS No.: 117-84-0)	CNS 15138-1 (民國101年) · 以氣相層析質譜儀分析。 / With reference to CNS 15138-1 (2012), analysis was performed by GC/MS.	%	0.003	n.d.	0.1
★鄰苯二甲酸二乙酯 / DEP (Diethyl phthalate) (CAS No.: 84-66-2)		%	0.003	n.d.	0.1
★高錳酸鉀消耗量-(水, 95°C, 30分鐘) / Potassium permanganate consumption-(water, 95°C, 30 min)	食品器具、容器、包裝檢驗方法-聚丙稀(PP)塑膠類之檢驗 (107年9月17日衛授食字第1071901787號公告) · / With reference to Methods of Test for Food Utensils, Containers and Packages - Test of Polypropylene (PP) Plastic Products (MOHW Food No. 1071901787 announced, September 17, 2018).	ppm	3	n.d.	10
★重金屬(以鉛計)-(4%醋酸, 95°C, 30分鐘) / Heavy metal (as Pb)-(4% acetic acid, 95°C, 30 min)		ppm	-	<1	1
★蒸發殘渣-(水, 95°C, 30分鐘) / Evaporation residue-(water, 95°C, 30 min)		ppm	3	n.d.	30
★蒸發殘渣-(4%醋酸, 95°C, 30分鐘) / Evaporation residue-(4% acetic acid, 95°C, 30 min)		ppm	3	n.d.	30
★蒸發殘渣-(正庚烷, 25°C, 1小時) / Evaporation residue-(n-Heptane, 25°C, 1 hr)		ppm	3	13	30 (*1)
★蒸發殘渣-(20%酒精, 60°C, 30分鐘) / Evaporation residue-(20% alcohol, 60°C, 30 min)		ppm	3	4	30
★鄰苯二甲酸二(2-乙基己基)酯 (正庚烷, 25°C, 1小時) / DEHP (Di-(2-ethylhexyl) phthalate) (CAS No.: 117-81-7) (n-Heptane, 25°C, 1 hr)		食品器具、容器、包裝檢驗方法-塑膠類之檢驗 (107年10月4日衛授食字第1071901983號公告) · 以氣相層析質譜儀分析。 / With reference to Methods of Test for Food Utensils, Containers and Packages - Test of Plastics (MOHW Food No. 1071901983 announced, October 04, 2018), analysis was performed by GC/MS.	ppm	0.05	n.d.
★鄰苯二甲酸二丁酯 (正庚烷, 25°C, 1小時) / DBP (Di-n-butyl phthalate) (CAS No.: 84-74-2) (n-Heptane, 25°C, 1 hr)	ppm		0.05	n.d.	0.3
★鄰苯二甲酸丁苯甲酯 (正庚烷, 25°C, 1小時) / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7) (n-Heptane, 25°C, 1 hr)	ppm		0.05	n.d.	30

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

測試報告

Test Report

號碼(No.): ETF20C00097

日期(Date): 31-Dec-2020

頁數(Page): 4 of 8

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)

新北市泰山區南林路102號 (NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN)

測試項目 (Test Item(s))	測試方法 (Method)	單位 (Unit)	LOQ/ LOD	結果 (Result)	限值 (Limit)
				No.1	
★鄰苯二甲酸二異癸酯 (正庚烷, 25°C, 1小時) / DIDP (Diisodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1) (n-Heptane, 25°C, 1 hr)	食品器具、容器、包裝檢驗方法-塑膠 類之檢驗 (107年10月4日衛授食字第 1071901983號公告) · 以氣相層析質 譜儀分析。/ With reference to Methods of Test for Food Utensils, Containers and Packages - Test of Plastics (MOHW Food No. 1071901983 announced, October 04, 2018), analysis was performed by GC/MS.	ppm	0.5	n.d.	9
★鄰苯二甲酸二異壬酯 (正庚烷, 25°C, 1小時) / DINP (Diisononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0) (n-Heptane, 25°C, 1 hr)		ppm	0.5	n.d.	9
★己二酸二(2-乙基己基)酯 (正庚烷, 25°C, 1 小時) / DEHA (Di-2-ethylhexyl Adipate) (CAS No.: 103-23-1) (n-Heptane, 25°C, 1 hr)		ppm	0.05	n.d.	18

備註(Note) :

- 檢驗報告僅就委託者之委託事項提供檢驗結果，不對產品合法性做判斷。(The test report merely reflects the test results of the consigned matters of the client and is not a certification of the legitimacy of the related products.)
- mg/kg = ppm ; 0.1wt% = 1000 ppm
- LOQ = Limit of Quantification (定量極限) ; LOD = Limit of Detection (偵測極限)
- n.d. = Not Detected (未檢出) = Less than (小於) LOQ/LOD
- "-" = Not Regulated (無規格值)
- (*1): 針對油脂及脂肪性食品用容器、包裝。(For containers and packages for oils and fatty foods.)
- 測試項目名稱旁有★者，為本實驗室通過衛生福利部食品藥物管理署認證項目。(The test method marked with ★ is accredited by MOHW.)
- 測試項目名稱旁有●者，為本實驗室擴充原方法適用基質，非屬食藥署該項認證範圍。(When there is a ● next to the test item, the test method was applied to the material out of the scope from MOHW accreditation.)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

測試報告 Test Report

號碼(No.): ETF20C00097


日期(Date): 31-Dec-2020

頁數(Page): 5 of 8

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)
新北市泰山區南林路102號 (NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN)

* 照片中如有箭頭標示，則表示為實際檢測之樣品/部位。*
(The tested sample / part is marked by an arrow if it's shown on the photo.)

ETF20C00097



** 報告結尾 (End of Report) **

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

測試報告 Test Report

號碼(No.): ETF20C00097

日期(Date): 31-Dec-2020

頁數(Page): 6 of 8

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)
 新北市泰山區南林路102號 (NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN)

以下為申請廠商委託測試項目、測試方法、定量/偵測極限：
 (The information requested from client is shown as below :)

ETF20C00097

測試項目 (Test Items)	測試方法 (Method)	LOQ/LOD
★鉛 / Lead (Pb)	食品器具、容器、包裝檢驗方法-聚丙烯(PP)塑膠類之檢驗 (107年9月17日衛授食字第1071901787號公告) · 以感應耦合電漿放射光譜儀分析。 / With reference to Methods of Test for Food Utensils, Containers and Packages - Test of Polypropylene (PP) Plastic Products (MOHW Food No. 1071901787 announced, September 17, 2018), analysis was performed by ICP-OES.	詳見測試結果之定量/偵測極限。(Please refer to the result table above.)
★鎘 / Cadmium (Cd)		
★鄰苯二甲酸二(2-乙基己基)酯 / DEHP (Di-(2-ethylhexyl) phthalate) (CAS No.: 117-81-7)	CNS 15138-1 (民國101年) · 以氣相層析質譜儀分析。 / With reference to CNS 15138-1 (2012), analysis was performed by GC/MS.	
★鄰苯二甲酸二丁酯 / DBP (Di-n-butyl phthalate) (CAS No.: 84-74-2)		
★鄰苯二甲酸丁苄甲酯 / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7)		
★鄰苯二甲酸二異癸酯 / DIDP (Diisodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1)		
★鄰苯二甲酸二異壬酯 / DINP (Diisononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0)		
★鄰苯二甲酸二甲酯 / DMP (Dimethyl phthalate) (CAS No.: 131-11-3)		
★鄰苯二甲酸二正辛酯 / DNOP (Di-n-octyl phthalate) (CAS No.: 117-84-0)		
★鄰苯二甲酸二乙酯 / DEP (Diethyl phthalate) (CAS No.: 84-66-2)		

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

測試報告

Test Report

號碼(No.): ETF20C00097

日期(Date): 31-Dec-2020

頁數(Page): 7 of 8

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)
 新北市泰山區南林路102號 (NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN)

以下為申請廠商委託測試項目、測試方法、定量/偵測極限：
 (The information requested from client is shown as below :)
 ETF20C00097

測試項目 (Test Items)	測試方法 (Method)	LOQ/LOD
★高錳酸鉀消耗量-(水, 95°C, 30分鐘) / Potassium permanganate consumption-(water, 95°C, 30 min)	食品器具、容器、包裝檢驗方法-聚丙稀(PP)塑膠類之檢驗 (107年9月17日衛授食字第1071901787號公告) 。 / With reference to Methods of Test for Food Utensils, Containers and Packages - Test of Polypropylene (PP) Plastic Products (MOHW Food No. 1071901787 announced, September 17, 2018).	詳見測試結果之定量/偵測極限。(Please refer to the result table above.)
★重金屬(以鉛計)-(4%醋酸, 95°C, 30分鐘) / Heavy metal (as Pb)-(4% acetic acid, 95°C, 30 min)		
★蒸發殘渣-(水, 95°C, 30分鐘) / Evaporation residue-(water, 95°C, 30 min)		
★蒸發殘渣-(4%醋酸, 95°C, 30分鐘) / Evaporation residue-(4% acetic acid, 95°C, 30 min)		
★蒸發殘渣-(正庚烷, 25°C, 1小時) / Evaporation residue-(n-Heptane, 25°C, 1 hr)		
★蒸發殘渣-(20%酒精, 60°C, 30分鐘) / Evaporation residue-(20% alcohol, 60°C, 30 min)		
★鄰苯二甲酸二(2-乙基己基)酯 (正庚烷, 25°C, 1小時) / DEHP (Di-(2-ethylhexyl) phthalate) (CAS No.: 117-81-7) (n-Heptane, 25°C, 1 hr)	食品器具、容器、包裝檢驗方法-塑膠類之檢驗 (107年10月4日衛授食字第1071901983號公告) 。 以氣相層析質譜儀分析。 / With reference to Methods of Test for Food Utensils, Containers and Packages - Test of Plastics (MOHW Food No. 1071901983 announced, October 04, 2018), analysis was performed by GC/MS.	
★鄰苯二甲酸二丁酯 (正庚烷, 25°C, 1小時) / DBP (Di-n-butyl phthalate) (CAS No.: 84-74-2) (n-Heptane, 25°C, 1 hr)		
★鄰苯二甲酸丁苯甲酯 (正庚烷, 25°C, 1小時) / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7) (n-Heptane, 25°C, 1 hr)		

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com.tw/terms-of-service> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <https://www.sgs.com.tw/terms-of-service>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

測試報告 Test Report

號碼(No.): ETF20C00097

日期(Date): 31-Dec-2020

頁數(Page): 8 of 8

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)
 新北市泰山區南林路102號 (NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN)

以下為申請廠商委託測試項目、測試方法、定量/偵測極限：
 (The information requested from client is shown as below :)

ETF20C00097

測試項目 (Test Items)	測試方法 (Method)	LOQ/LOD
★鄰苯二甲酸二異癸酯 (正庚烷, 25°C, 1小時) / DIDP (Diisodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1) (n-Heptane, 25°C, 1 hr)	食品器具、容器、包裝檢驗方法-塑膠類之檢驗 (107年10月4日衛授食字第1071901983號公告) · 以氣相層析質譜儀分析。/ With reference to Methods of Test for Food Utensils, Containers and Packages - Test of Plastics (MOHW Food No. 1071901983 announced, October 04, 2018), analysis was performed by GC/MS.	詳見測試結果之定量/偵測極限。(Please refer to the result table above.)
★鄰苯二甲酸二異壬酯 (正庚烷, 25°C, 1小時) / DINP (Diisononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0) (n-Heptane, 25°C, 1 hr)		
★己二酸二(2-乙基己基)酯 (正庚烷, 25°C, 1小時) / DEHA (Di-2-ethylhexyl Adipate) (CAS No.: 103-23-1) (n-Heptane, 25°C, 1 hr)		

測試項目名稱旁有★者，為本實驗室通過衛生福利部食品藥物管理署認證項目。(The test method marked with ★ is accredited by MOHW.)

測試項目名稱旁有●者，為本實驗室擴充原方法適用基質，非屬食藥署該項認證範圍。(When there is a ● next to the test item, the test method was applied to the material out of the scope from MOHW accreditation.)